



FLAME CONTROL NO. 40-40A

A Water Base

Low-Gloss Fire Retardant Paint (Overcoat)
Fire Hazard Classification, CLASS "A"

DESCRIPTION:

Flame Control No. 40-40A is a Class "A", low-gloss, interior-exterior (*) general purpose latex, (water base) coating. It is rated for use on noncombustible surfaces, and as a topcoat for Flame Control Intumescent Fire Retardant Paint. It dries quickly to yield a highly cleansible-scrubbable water resistant film that possesses excellent adhesion, flexibility and toughness. No. 40-40A is suitable for application to all interior surfaces (except floors and shelving).

(*) Exterior application: May be used on exterior masonry surfaces where a highly water resistant, decorative, fire retardant coating is desired.

RECOMMENDED USES:

Interior: For use on all noncombustible surfaces (except floors and shelving) and as an overcoat for Flame Control Intumescent Fire Retardant Paint, where a low-gloss highly cleansable coating is desired. Exterior: For use on masonry surfaces where a flame retardant coating is required.

USED BY:

Schools, Colleges, Nursing Homes, Child Care Centers, Hospitals, Penal Institutions, Apartments, Hotels, Factories, Warehouses, Retail Stores, Restaurants, Utilities, Railroad and other Transportation Companies, Oil and Chemical Installations, Military Installations, and other facilities where fire retardant coatings are required.

PERFORMANCE INFORMATION:

- Class "A" fire rated on noncombustible surfaces. (see fire hazard classification section).
- Class "A" fire rated as a topcoat for intumescent fire retardant paint. (see fire hazard classification section)

- Complies with federal, state, local building and fire code requirements.
- Dries by water evaporation to a tough, flexible, low-gloss finish.
- Does not leach (lose fire retardant properties) on exposure to high humidity.
- Meets all current environmental regulations.

CHARACTERISTICS:

Finish . Low-gloss, 15-20 units @ 60°

Color White, Off-White and 13 standard pastel colors

Tinting . . Can be tinted with up to 4 fl. oz. of Universal Tint. Check colorant for compatibility.

Spreading

Rate 350 to 625 sq. ft./gal.
(8.6 to 15.3 m²/L)
2.6 to 4.6 mils wet, 1.0 to 1.8 mils dry,
depending on substrate.

Volume Solids 40% ± 2

Weight Solids 55% ± 2

V.O.C. Less

Than 1.5 lbs./gal. (185 g/L)

Drying Time @

77°F & 50% RH: . . To touch 30 min.
To handle 1 hours
To recoat 1 to 2 hours

Type of Cure Coalescence

Flash Point None
(Pensky-Martens Closed Cup)

Reducer/Cleaner Water

Shelf Life 1 year (unopened)

Packaging 1 & 5 gal. containers
weight/gal. 10.8 ± 0.2 lbs.

Shipping weight 4 gals - 48 lbs.
5 gals - 56 lbs.

Application Brush, roller,
and airless spray

PRECAUTIONS:

Adequate ventilation must be provided during and after application until the coating has dried. Avoid breathing vapors or spray mist. Close container after use. DO NOT TAKE INTERNALLY.

Read MSDS before opening containers.

KEEP OUT OF REACH OF CHILDREN

SURFACE PREPARTION:

Surface preparation should be carried out according to good painting practices. Remove all loose, peeling or powdery paint from the surface. All dirt, grease, oil, wax and other foreign matter MUST be removed with a detergent. Rinse surfaces thoroughly with clear water and allow to dry. Repair all cracks, holes and other surface irregularities. Allow to dry, sand lightly and prime repaired surfaces with No.40-40A.

NEW SURFACES:

Can be applied directly to primed steel and directly to all other noncombustible surfaces; i.e., dry wall, plaster board, plaster and masonry surfaces. All combustible surfaces, such as wood, plywood, fiberboard, etc., must be coated with Flame Control Intumescent Fire Retardant Paint, before application of No. 40-40A. New ferrous metal surfaces must be primed. Apply Temperkote® H₂O Primer. Allow to dry 3-4 hours or until hard, before applying No. 40-40A.

PREVIOUSLY PAINTED SURFACES:

Noncombustible surfaces having excessive conventional paint film build up, and all combustible surfaces, such as wood, plywood, fiberboard, etc., must be coated with Flame Control Intumescent Fire Retardant Paint, before application of No. 40-40A.



FLAME CONTROL NO. 40-40A

A Water Base

Low-Gloss Fire Retardant Paint (Overcoat)
Fire Hazard Classification, CLASS "A"

No. 40-40A may be applied directly to existing paint that is tightly adherent and in good condition. All glossy surfaces should be dulled with sandpaper. Spot prime where necessary with appropriate primer as shown above, before application of No. 40-40A.

APPLICATION:

Mix paint thoroughly by boxing or stirring. Flame Control No. 40-40A can be applied by brush, roller, airless or conventional heavy duty spray equipment. Apply using a full bodied coat at the recommended coverage rates. To conform with surface burning characteristics established for this paint, dilution of the paint should be compensated with reduced coverage rates. Do not apply when surface or air temperatures are below 50°F (10°C). Protect from freezing.

APPLICATION EQUIPMENT:

Airless Spray

Titan 440 Impact (or Equivalent)

- Pump
- Fluid Pressure. 2250-2700 psi
- Manifold Filter 60 Mesh
- Gun Filter 60 Mesh
- Fluid Hose ¼" diameter
- Gun LX-80 II
- Tip.017 - .023
- Reduction Up to 7%

FIRE HAZARD CLASSIFICATION

Flame Spread Rating, Class "A" when tested in accordance with ASTM E-84 (NFPA 255), the coating obtained the following hazard classification.

COATING (SYSTEM) DETAILS	CLASSIFICATION OR RATING (WHEN APPLIED TO DOUGLAS FIR)	
	Flame Spread	Smoke Developed
PRIMER – None BASE COAT – Type 10-10 applied in one coat at 190 sq. ft./U.S. gal. (4.7 m ² /L) TOP COAT – Type 40-40A applied in one coat at 625 sq. ft./U.S. gal (15.3 m ² /L)	10	15

Flame Spread Rating, Class "A" when tested in accordance with ASTM E-84 (NFPA 255), the coating obtained the following fire hazard classification.

COATING (SYSTEM) DETAILS	CLASSIFICATION OR RATING (WHEN APPLIED TO INORGANIC-CEMENT BOARD)	
	Flame Spread	Smoke Developed
PRIMER – None BASE COAT – Type 40-40A applied in one coat at 330 sq. ft./U.S. gal. (8.1 m ² /L)/coat TOP COAT – None	0	0

As we cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used, we accept no responsibility for results obtained by the application of this information or the safety or suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. We sell the products without warranty or guarantee, and buyers and users assume all responsibility and liability for loss or damage from the handling and use of our products, whether used alone or in combination with other products.